



# Winston Battery

Address: Winston Industrial Park, Third Industrial Zone, Lisonglang Village,  
Gongming Town, Shenzhen, Guangdong, P.R.C  
Tel: +86-755-8602 6789 Fax: +86-755-8602 6678  
Http: //www.winston-battery.com E-mail: winston@winston-battery.com


## 溫斯頓牌稀土鋰鈮動力電池性能說明

SPECIFICATION FOR WINSTON RARE EARTH LITHIUM YTTRIUM POWER BATTERY

### 單體電池尺寸 DIMENSIONS



型号(MODEL): WB-LYP300AHA




### 技術參數 SPECIFICATIONS

型號(MODEL)	WB-LYP300AHA		
標稱容量 Nominal Capacity	300AH		
規格 SPEC	長 L	362mm	
	寬 W	55.5mm	
	高 H	306mm	
工作電壓 Operation Voltage	充電 Charge	4.0(V)	
	放電 Discharge	2.8(V)	
內阻 Internal resistance	≤0.3(mΩ)		
最大放電電流 Max Discharge Current	恒電流 Constant Current	≤3CA	
	脈衝試 Impulse Current	≤10CA	
最大充電電流 Max Charge Current	900A(3CA)		
標準充放電電流 Standard Charge/ Discharge Current	150A(0.5CA)		
循環壽命 Cycle Life	(80%DOD)	≥5000Times	
	(70%DOD)	≥7000Times	
殼體耐溫性 Temperature Durability Of Case	≤200°C		
	適應環境 Operationg Temperature	充電 Charge	-45°C ~ 85°C
	放電 Discharge		
	存儲濕度 Storage Humidity	≤75%RH	
自放電率(月) Self-discharge Rate	≤3% (月/Monthly)		
單體電池重量 Weight	9.7kg ± 250g		


# WB-LYP300AHA型電池的充放電特性

## WB-LYP300AHA CHARGE & DISCHARGE CHART


常溫下LYP類電池的放電特性曲線  
LYP battery's discharge curve under normal temperature



常溫下LYP類電池的循環充放電特性曲線  
LYP battery's circulation charging and discharging curve under normal temperature



不同環境溫度下LYP類電池的放電特性曲線  
LYP battery's discharge curve under different temperatures



在常溫境溫下LYP類電池的存儲特性曲線  
LYP battery's storage characteristic curve in normal temperature

